

Pride 100% Acrylic Exterior Latex Semi-Gloss House Paint

8-3501 Series

DESCRIPTION

Our finest exterior acrylic latex semi-gloss house paint resists blistering, peeling and chalking. It has a weather resistant semi-gloss finish, one coat coverage, and exclusive adhesion properties. This product is designed for use on wood and aluminum siding, masonry, brick, cement block, asbestos shingles, wood trim and properly primed metal.



FEATURES

- 100% acrylic for maximum durability and scrubability
- Resists peeling, blistering and chalking
- Ideal for aluminum siding
- Protects the surface from weather
- Can be applied when air temps are as low as 45° F

VOC / MIR (sprays)

100 gm/l
(0.83 lbs/gal)

NET WEIGHT

8.99 - 9.95 lbs/gal

AVAILABLE SIZES

5-gallon, gallon,
quart

SHIPPING WT

5-gal pail/60 lbs
4-gal case/45 lbs
4-qt case/12 lbs

AVAILABLE COLORS

8-3501 High Hiding White, 8-3510 Brilliant White, 8-3581 White TB #1, 8-3582 Midtone TB #2, 8-3583 Deep TB #3, 8-3584 Neutral TB #4, 8-3589 Happy Trail

SHIPPING RESTRICTION

CA - Gal & 5 Gal

PRODUCT STATISTICS

DRYTIME-TOUCH 1/2 to 1 hour	DRYTIME-RECOAT 8 hours	WET/ FILM THK 3.0 mils	FILM THK /DRY: 1.0 mils	FINISH Semi-Gloss	GLOSS 40-50 @ 60°
FLASHPOINT > 200°F	COVERAGE Up to 400 sq ft/gal	VISCOSITY 85 - 90 KU	VEHICLE Acrylic Latex	SOLVENT Water	

SURFACE PREP

New Wood: Prime with an alkyd exterior primer or acrylic primer. Allow 24 hours drying time. Putty nail holes and caulk all cracks and open seams. Cedar or Redwood may require two primer coats to prevent bleed through. Previously Painted Wood: Remove all loose or peeling paint with scraper or sander. Remove any mildew with a solution of trisodium phosphate, bleach and water. Rinse thoroughly and let dry. Wear goggles and gloves to prevent contact with the trisodium phosphate and bleach. Sand all glossy areas. Wash and rinse to remove dirt and chalk. Let dry completely. Spot prime bare areas with and exterior primer. Replace all brittle or cracked caulking. Previously Painted Masonry: Remove all loose or powdery paint and caulk. Spot prime bare areas with this product. New Masonry: Apply two coats of this product. Newly poured concrete should weather for 90 days and be etched with a 10% muriatic acid solution if it is smooth. Wear goggles and gloves to prevent contact with the muriatic acid. Metal Surfaces: Prime iron or steel with a metal primer. Prime unprotected galvanized metal with an acrylic primer. Aluminum Siding: Remove all chalk or loose paint. Clean surface thoroughly with an aluminum siding cleaner. Apply two coats of this product.

APPLICATION

Stir paint thoroughly. Apply generously with a nylon or polyester brush. For large areas use a medium nap roller. Do not paint in direct sunlight. On hot days surface may be dampened with water prior to painting to keep paint from drying too quickly. Stop painting at least four hours before nightfall. This product may be applied when air and surface temperatures are as low as 45° F and are expected to remain as such for a period of 48 hours after application. Do not paint if rain is expected within 24 hours. Apply two coats for a longer lasting paint job. If using two or more gallons of the same color, mix together and stir paint thoroughly to make sure color is uniform though out.

WARNING

If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Yenkin-Majestic Paint Corp. 1920 Leonard Ave. Columbus, OH 43219 Ph: (800) 848-1898 Fx: (614) 258-3062

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and due to variations in user handling and application methods should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, express or implied, concerning this product or its use either singly or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user assures that workplace and disposal practices are in compliance with laws, regulations and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

REVISED DATE 11/11/2015