

MAJIC® TOWN & COUNTRY® Tractor, Truck & Implement Enamel

FEATURES

- Outstanding durability
- Corrosion resistance
- Excellent adhesion
- Lasting high gloss finish
- VOC compliant in all states

DESCRIPTION & USES

Majic Oil Base High Gloss Paint is a durable oil-based finish formulated with the finest quality oils and pigments for outstanding performance on exterior wood and metal. It applies easily with brush, roller or spray. Use it on: Wood siding, masonry, brick, properly primed metal, and previously painted surfaces.

PRODUCTS & SIZES

Gallons and quart sizes standard. 24 ready-mix colors. Also available in matching 11 oz. aerosol cans. 8-0750-3 Majic Reducer available in pint size. 8-0950-4 Majic Catalyst Hardener available in half-pint size.

SURFACE PREPARATION

Bare Metal: Remove all rust scale with wire brush or sander. Remove oil or grease with paint thinner. Prime with rust-inhibiting primer, either #8-0986 Majic Tractor, Truck & Implement Gray Primer or #8-0989 Red Oxide Primer. **Painted Metal:** Remove loose or peeling paint and rust scale with wire brush or sander. Remove oil or grease with paint thinner. Prime any bare areas. **Painted Surfaces:** (General) Make sure surface is clean, dry and free of loose paint, dirt, wax, grease, etc. Sand glossy areas. Spot prime absorbent areas.

APPLICATION

Stir thoroughly. Apply with a high-quality brush, roller paint pad, or by conventional spray equipment. Apply one or two coats, allowing each coat to dry thoroughly before applying the next coat. Lightly sand between coats. Do not apply if surface temperature is below 50°F (10°C) or in direct sun light. To spray, add one pint of #8-0750 Majic Reducer per gallon of Tractor, Truck & Implement topcoat. The addition of Majic Reducer will give the perfect spray consistency without compromising VOC limits. For a harder, higher gloss and faster curing finish, add ½ pint of #8-0950 Majic Catalyst Hardener to each gallon of Tractor, Truck & Implement Enamel. Majic Reducer and Majic Catalyst Hardener can be added together for spraying.

Spray Equipment: For conventional spray use Graco 700 Gun 217-757 equipment or equivalent, with fluid pressure of 20 lbs. and atomizing pressure of 35-40 lbs. For airless spray use a .013" to .019" orifice with 1,850 psi at tip.

Drying: Normal drying is 5 to 10 hours at 77F (25C) and 50% humidity. Allow 24 hours between coats.

Note: DO NOT OVER-APPLY. Proper drying and curing time may significantly slow if applied in excess of 2.5 mils wet, or if recoating too soon.

Clean Up: Mineral spirits immediately after use.

PHYSICAL PROPERTIES

RESIN TYPE	Alkyd
SOLVENT	Mineral Spirits
GLOSS	80% + @ 60°
VOC	<340 grams/liter
FILM THICKNESS	2.5 Mils Wet 1.4 Mils Dry
COVERAGE	600-700 sq ft/gal
DRY TIMES AT 77°F AND 50% RELATIVE HUMIDITY	5 - 10 Hours To Touch 24 Hours To Recoat 7-14 Days Full Cure
WEIGHT SOLIDS	70% ± 2%
VOLUME SOLIDS	57% ± 2%
FLASH POINT	>105°F

Majic Paints • 201 Janus Road • Cary, IL 60013 • 847-639-5383 • www.majicpaints.com

Caution:

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and, due to variations in user handling and application methods, should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, expressed or implied, concerning this product or its use either individually or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user ensures that workplace and disposal practices are in compliance with laws, regulations, and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENT OR CONSEQUENTIAL DAMAGES.