

## MAJIC® PRIDE

### Exterior Semi-Gloss Paint & Primer

#### FEATURES

- 100% acrylic for maximum durability and washability
- Ideal for aluminum siding
- Protects the surface from weather
- Resists peeling, blistering and chalking
- Can be applied when air temps are as low as 45°F

#### DESCRIPTION & USES

Our finest exterior acrylic latex semi-gloss house paint resists blistering, peeling and chalking. It has a weather resistant semi-gloss finish, one coat coverage, and exclusive adhesion properties. This product is designed for use on wood and aluminum siding, masonry, brick, cement block, asbestos shingles, wood trim and properly primed metal.

#### PRODUCTS & SIZES

8-3510 Brilliant White, 8-3581 White TB #1, 8-3582 Midtone TB #2, 8-3583 Deep TB #3, 8-3584 Neutral TB #4. Available in quarts, gallons and 5 gallons.

#### SURFACE PREPARATION

**New Wood:** Prime with an alkyd exterior primer or acrylic primer. Allow 24 hours drying time. Putty nail holes and caulk all cracks and open seams. Cedar or Redwood may require two primer coats to prevent bleed through. **Previously Painted Wood:** Remove all loose or peeling paint with scraper or sander. Remove any mildew with a solution of trisodium phosphate, bleach and water. Rinse thoroughly and let dry. Wear goggles and gloves to prevent contact with the trisodium phosphate and bleach. Sand all glossy areas. Wash and rinse to remove dirt and chalk. Let dry completely. Spot prime bare areas with and exterior primer. Replace all brittle or cracked caulking. **Previously Painted Masonry:** Remove all loose or powdery paint and caulk. Spot prime bare areas with this product. **New Masonry:** Apply two coats of this product. Newly poured concrete should weather for 90 days and be etched with a 10% muriatic acid solution if it is smooth. Wear goggles and gloves to prevent contact with the muriatic acid. **Metal Surfaces:** Prime iron or steel with a metal primer. Prime unprotected galvanized metal with an acrylic primer. **Aluminum Siding:** Remove all chalk or loose paint. Clean surface thoroughly with an aluminum siding cleaner. Apply two coats of this product.

#### APPLICATION

Stir paint thoroughly. Apply generously with a nylon or polyester brush. For large areas use a medium nap roller. Do not paint in direct sunlight. On hot days surface may be dampened with water prior to painting to keep paint from drying too quickly. Stop painting at least four hours before nightfall. This product may be applied when air and surface temperatures are as low as 45° F and are expected to remain as such for a period of 48 hours after application. Do not paint if rain is expected within 24 hours. Apply two coats for a longer lasting paint job. If using two or more gallons of the same color, mix together and stir paint thoroughly to make sure color is uniform though out.

#### PHYSICAL PROPERTIES

RESIN TYPE	Acrylic Latex
SOLVENT	Water
GLOSS	40-50 @ 60°
VOC	<100 grams/liter
FILM THICKNESS	3.0 Mils <b>Wet</b> 1.0 Mils <b>Dry</b>
COVERAGE	Up to 400 sq ft/gal
DRY TIMES AT 77°F AND 50% RELATIVE HUMIDITY	0.5 - 1 Hour <b>To Touch</b> 8 Hours <b>To Recoat</b> 7-10 Days <b>Full Cure</b>
VISCOSITY	85-90 KU
FLASH POINT	> 200°F
FINISH	Semi-Gloss

**Majic Paints • 201 Janus Road • Cary, IL 60013 • 847-639-5383 • [www.majicpaints.com](http://www.majicpaints.com)**

#### Caution:

**WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

The information and specifications stated here are for the material currently offered, are subject to change without prior notice, and, due to variations in user handling and application methods, should not be relied upon without testing under user conditions. The supplier makes no warranty of any kind, expressed or implied, concerning this product or its use either individually or in combination with other substances. User assumes all risks incident to its use. User must communicate to employees and customers all warnings that relate to the potential exposure to this product. The user ensures that workplace and disposal practices are in compliance with laws, regulations, and ordinances. ALL WARRANTIES, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE EXPRESSLY EXCLUDED. IN NO EVENT SHALL THE SUPPLIER BE LIABLE FOR ANY INCIDENT OR CONSEQUENTIAL DAMAGES.